

ELASTIDEN PLUS

Viscous elastomeric bituminous liquid sheath

Description: Liquid waterproofing membrane formulated with bitumen, elastomeric resins, and selected solvents.

Advantages:

- Waterproofs concrete surfaces affected by micro-cracks or subjected to thermal expansion.
- Once dried, it forms a waterproof, elastic, and tough film.
- Easy spreading on the laying surface both vertically and horizontally.
- Adapts to any surface geometry to be coated.
- Quicker drying compared to the bituminous emulsions.
- Excellent resistance to standing water on the surface even in the absence of a slope.
- Frost resistant.
- Resistant to low temperatures: can also be used in winter.
- Excellent resistance on surfaces in industrial areas or near the sea.

Applications: Suitable for coating and waterproofing:

- Old bituminous membranes
- Flat, non-walkable roofing on concrete surfaces
- Underground and foundation walls
- Concrete structures for liquid containment.
- Sheet metal roofing
- Roof details.
- Fibre-cement, wood, polycarbonate, and metallic surfaces.

Surface preparation:

- Make sure that the surface is free from detached parts, loose debris or non-adherent parts, coatings, rust, powder, or release oils. Carefully clean the surfaces, which must be solid, even, and dry and in the case of concrete surfaces must not have been previously treated with evaporation retardant products. Avoid application if bad weather is forecast, as it could negatively affect the proper drying of the product.
- Do not apply to wet or damp surfaces.
- Before applying, check that waterproofing ensures proper run-off of rainwater.
- Apply at temperatures between -10 °C and +35 °C; avoid extremely hot or cold conditions during application and drying of the film.

Application:

- Mix the product before use.
- Apply by airless spray (the product can be diluted with nitro thinners or common solvent-based bitumen primers), brush, broom or roller.
- On surfaces larger than 10 m² or mechanically stressed supports, we recommend reinforcing Elastiden Plus with suitable non-woven polyester fabric, embedded in the first still fresh coat. For this specific application in combination with non-woven fabric, always use the diluted product (in both layers of application) up to 3%, with common solvent-based bituminous primers or thinners available in the market.
- Use common synthetic thinners to clean tools.

Consumption:

- We recommend applying at least 2 coats, the next one when the previous one is perfectly dry.
- The consumption of the product depends on the surface and the desired thickness but usually varies between 1.2 and 1.4 kg/m² overall. On average, to obtain a 1 mm dry film, the quantity of product used will be approximately 1.4 kg/m².

ELASTIDEN PLUS**Viscous elastomeric bituminous liquid sheath****Warnings:**

- Do not use indoors or in non-ventilated premises.
- We recommend not to exceed the above-mentioned consumption, as this could lead to an imperfect drying of the film in depth, due to the persistence, under the surface layer, of fractions of unevaporated solvent (this effect is due to the total waterproofness of the film dried on the surface, which prevents normal evaporation of the solvent).
- If the applied product remains visible, the dried film should be protected with reflective paints or coloured decorative paints. We recommend painting only a few months after its application.
- Check (according to UNI 10329) that the residual humidity content of the cement surface to be treated is $\leq 5\%$ by weight (for screeds with a density of 2000 kg/m^3).
- When waterproofing containment tanks for liquids, we recommend applying the product in combination with suitable non-woven fabric reinforcement.
- Apply the product on the side of the structure exposed to water (water stress under positive pressure).
- Do not use to coat surfaces in contact with drinking water or edible liquids.
- Do not use on surfaces subject to rising damp or strong water pressure.
- Do not apply on very hot surfaces, which would adversely affect the product's cohesion and adhesion to the surface.
- It can be stepped on in case of occasional maintenance.
- Flammable product. Store in tightly sealed original packaging.
- Do not expose to temperatures over 30°C , heat sources, open flames or other sources of ignition.
- Comply with the information on the safety data sheet.
- Consult the information at the bottom of this document.

Packaging:

1, 5, 10, and 20 kg metal pails.
200 kg metal drums.

Packaging:

Elastiden Plus Antiradice is available; it is a version of the product with the addition of special additives that make it ideal for waterproofing surfaces in contact with plants, flowers, and vegetation in general.

Technical data:

MAIN CHARACTERISTICS		
Appearance		Liquid
Colour		Black
Shelf life in closed original packaging		24 months
Closed-cup flash point	ASTDM 3828-87	> +23 °C
Solid content (<i>m/m at 130 °C</i>)	EN ISO 3251	(64-72)%
Brookfield viscosity (<i>at 25 °C, spindle 3; 10 rpm</i>)	EN ISO 3219	(16,500±3,000)cP
Density (<i>at 20 °C</i>)	EN ISO 2811-1	(1.00-1.06) kg/L
Tack-free time		90 - 120 minutes*
Drying time for recoating		24-48 hours*
Flexibility at low temperatures	EN 15813	-15 °C
PERFORMANCE PROPERTIES - EN 1504-2 SURFACE PROTECTION SYSTEMS FOR CONCRETE (C COATINGS – PRINCIPLES: PI-MC-IR)		
Permeability to CO ₂	EN 1062-6	S _D > 50 m
Water vapour permeability	EN ISO 7783	Class I (S _D < 5 m)
Liquid water permeability	EN 1062-3	w < 0.1 kg/m ² ·h ^{0.5}
Tensile bond strength	EN 1542	≥ 1 N/mm ²
Reaction to fire	EN 13501-1	E

* Measurements have been recorded at a temperature of 23 °C and with 50% moisture. Declared data may vary depending on the thickness of the applied product and on the specific conditions of the construction site: temperature, humidity, ventilation, and absorptency of surfaces.



The advice and technical information provided represent HA ITALIA S.p.A.'s best knowledge of product properties and use. Considering the different situations of use of the products and factors beyond our control (media, working conditions, failure to comply with instructions), we cannot be held responsible for the results obtained. Before using the product, anyone who intends to make use of it is required to determine whether it is suitable for the intended use and assumes full liability for whatever may arise from its use.

HA Italia disclaims any and all liability arising from failure to observe the warnings mentioned in this data sheet and failure to comply with the requirements set out in the safety data sheet.

Data sheet no.: 20004336-REV01 dated 01.01.2024