

- Description:Mixture of selected high molecular weight bitumen in the form of loaves wrapped in a
polyethylene film.Advantages:Contains no hazardous substances
- Applications: Protective for cement surfaces
 Connection layer between cement surfaces and compatible heat-insulating materials
 Connection layer between compatible heat-insulating materials
- Packaging: Polyethylene bags of 25 kg each.

Technical data:

MAIN CHARACTERISTICS		
Appearance		Solid
Penetration (at 25 °C)	EN 1426	(10-20) dmm
Softening point	EN 1427	(85-110) °C
Density (at 20 °C)	EN ISO 2811-1	(1.00 ± 0.03) kg/L
Viscosity (at 60 °C)	EN ISO 12595	>1000 mm ² /s
Flash point	EN ISO 2592	> 250 °C
Melting point	EN 1427	> 50 °C
Autoignition temperature	ASTM 659	> 400 °C

HA Italia disclaims any and all liability arising from failure to observe the warnings mentioned in this data sheet and failure to comply with the requirements set out in the safety data sheet.

Data sheet no.: 20004094-REV01 dated 01.01.2023



HA ITALIA S.p.A. DIVISIONE PRODOTTI SPECIALI

Viale della Scienza 78 -80 - 36100 Vicenza - Italy Stabilimento Via Vicenza 72 - 36015 Schio (VI) P.I. e C.F. IT00169590247 - Ph +39 0445 678000 info@ha-italia.com - www.ha-italia.com - in ha italia s.p.a - 🚹 ha italia s.p.a



The advice and technical information provided represent HA ITALIA S.p.A.'s best knowledge of product properties and use. Considering the different situations of use of the products and factors beyond our control (media, working conditions, failure to comply with instructions), we cannot be held responsible for the results obtained. Before using the product, anyone who intends to make use of it is required to determine whether it is suitable for the intended use and assumes full liability for whatever may arise from its use.